

Data sheet

ENGLISH

Superwool® XTRA Pyro-Stack Modules

Product data - Page 2

Description

Pyro-Stack modules comprise strips of high quality spun fibre blanket, compressed and banded with plastic strips and including two stainless steel tubes mounted transversely through the strips remote from the hot face. They can be anchored to the furnace casing in any one of four standard versions, Y, M, and T.

In the Y module, the tubes are connected with a central, internal yoke, which includes a stainless steel stud and aluminium extension tube. This version is installed directly onto a metal plate casing, without pre-welding, using the special Pyro Bloc stud gun. It offers the fastest installation rates of any currently available modules.

The M module also includes the central yoke, which is fitted onto pre-welded studs using the special M module stud locating equipment.

The T module is anchored with a pre-studded, external, side-fix yoke.

M and T modules are used where the lining specification calls for either or both a backing blanket and anticorrosion treatment of the casing.

Type

Stacked blanket anchored modules.

Classification temperature

Superwool® XTRA Modules: 1450°C (EN 1094-1) 2600°F (ASTM C892-17)

Maximum continuous use temperature

Superwool® XTRA Fibre: 1300 - 1325°C (2372 - 2417°F)

The maximum continuous use temperature depends on the application. The wide range of available densities and thicknesses allow for the most effective deployment of the superior thermal characteristics in a wide variety of applications.

For further advice please contact your local Thermal Ceramics partner.

Features

Pyro-Stack modules combine some of the features of Pyro-Bloc and convoluted blanket modules:

- The Pyro-Stack module maintains the lightweight, thermal efficiency and resistance to thermal shock, which are characteristic of ceramic fibre linings
- They share the flexibility of anchorage and ease of installation of the Pyro-Bloc modules the decompression of the blanket gives tightly sealed inter-modular joints
- The resilience of the blanket can accommodate some flexing of the furnace casing without opening gaps between modules
- The resilient blanket is resistant to mechanical damage
- Y Modules – Fast installation. All welds automatically torque tested. One-step installation
- M and T Modules – Allow use of backing insulation and casing treatment. Module compression guaranteed. Simple fixing components. Use standard, commercially available welding equipment

Benefits

There are some specific benefits of using Superwool® XTRA Pyro-Stack modules:

- Excellent thermal insulating performances
- Exonerated from any carcinogenic classification under nota Q of directive 97/69EC, certificate available on request
- Does not form crystalline silica when exposed to high temperatures
- Excellent resistance to chemicals and pollutants, especially alkali metals
- High thermal coefficient of expansion to counteract shrinkage in operation
- Excellent thermal stability with time
- Low heat storage
- Immune to thermal shock
- High resistance to erosion when used in stack modules; no damage up to 50 m/sec at 1250°C (2282°F)
- Resistant to water and steam
- Good sound absorption

Data sheet

Product data

Superwool® XTRA Pyro-Stack Modules

Physical properties		Superwool® XTRA Pyro-Stack Modules		
Classification temperature	°C (°F)	1450 (2600)		
Melting point	°C (°F)	1650 (3000)		
Typical properties				
Colour		White		
Density	kg/m ³ (pcf)	170 (10.6), 192 (12), 210 (13.1)		
Modulus of Rupture, Mpa (psi)		Flexible		
High temperature performance				
Maximum continuous use temperature	°C (°F)	1300 - 1325 (2372 - 2417)		
Shrinkage @ 1450°C (2642°F) (modified EN 1094-1 method)		<4%		
Module density availability	kg/m ³ (pcf)	170 (10.6), 192 (12), 210 (13.1)		
Erosion resistance @ 1250°C (2282°F)		No damage up to 50 m/sec		
Thermal conductivity W/m.K, (ASTM C-201) (BTU in/hr ft ² °F) at mean temperature of:		170kg/m³	192kg/m³	210kg/m³
	200°C (390°F)	0.08 (0.56)	0.08 (0.56)	0.08 (0.56)
	400°C (750°F)	0.11 (0.76)	0.11 (0.76)	0.12 (0.83)
	600°C (1110°F)	0.18 (1.25)	0.19 (1.32)	0.19 (1.32)
	800°C (1470°F)	0.28 (1.94)	0.29 (2.01)	0.29 (2.01)
	1000°C (1830°F)	0.42 (2.91)	0.44 (3.05)	0.42 (2.98)
	1200°C (2190°F)	0.59 (4.09)	0.61 (4.23)	0.61 (4.23)

Fixing components and installation

The standard tubes and yokes for all Pyro-Stack modules are ASTM 316 stainless steel, but higher grades of steel (ASTM 310 or Inconel 601) are available for more arduous service conditions. Studs are ASTM 304 stainless steel or of such higher grade which are warranted by the service conditions.

Full details of the installation of all Morgan Thermal Ceramics modules are included in our Module Installation Manual.

Availability and packaging

Pyro-Stack modules are normally supplied as 305mm square and of thicknesses ranging from 100mm to 350mm, in 25mm increments. Other sizes, shapes and densities, including L-shaped modules can be made available on request.

Pyro-Stack modules are delivered packed either in cartons 315mm square x 930mm long or on palletted jumbo cartons, 1250mm x 1110mm x 1100mm high (including pallet).

Contact

Europe:

Telephone:
+44 (0) 151 334 4030

E-mail:
marketing.tc@morganplc.com

North America:

Telephone:
+1 (706) 796 4200

E-mail:
northamerica.tc@morganplc.com

South America:

Telephone:
+54 (11) 4373 4439

E-mail:
marketing.tc@morganplc.com

Asia:

Telephone:
+65 6595 0000

E-mail:
asia.mc@morganplc.com

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.

SUPERWOOL® is a patented technology for high temperature insulation wools which have been developed to have a low bio persistence (information upon request). **SUPERWOOL®** products may be covered by one or more of the following patents, or their foreign equivalents:

SUPERWOOL® PLUS and **SUPERWOOL® HT** products are covered by patent numbers:
US5714421 and US7470641, US7651965, US7875566, EP1544177 and EP1725503 respectively.

SUPERWOOL® XTRA products are covered by patent number: US8088701 and EP2086897B1.

A list of foreign patent numbers is available upon request to Morgan Advanced Materials plc.

Morgan Advanced Materials plc Registered in England & Wales at Quadrant, 55-57 High Street, Windsor, Berkshire SL4 1LP UK Company No. 286773